

Technical Data Sheet

Ultracur3D® EPD 1086

Daylight | General Purpose | Black

General Properties	Norm	Typical Values
Appearance	-	Black
Viscosity, 30°C	Cone/Plate Rheometer ¹⁾	450 mPas
Viscosity, 50°C	Cone/Plate Rheometer ¹⁾	130 mPas
Density (printed part)	ASTM D792	1.18 g/cm ³

Tensile Properties	Norm (5 mm/min)	Typical Values
E Modulus	ASTM D638	1810 MPa
Ultimate Tensile Strength	ASTM D638	42 MPa
Elongation at Break	ASTM D638	26%

Flexural Properties	Norm	Typical Values
Flexural Modulus	ASTM D790	1620 MPa
Flexural Strength	ASTM D790	67 MPa

Impact Properties	Norm	Typical Values
Notched Izod (Machined), 23°C	ASTM D256	28 J/m
Unnotched Izod, 23°C	ASTM D256	606 J/m
Charpy notched, 23°C	ISO 179-1	2.6 kJ/m ²

Thermal Properties	Norm	Typical Values
HDT at 0.45 MPa	ASTM D648	53°C
HDT at 1.82 MPa	ASTM D648	46°C
Flammability	UL 94 1.5 mm	HB

Hardness	Norm	Typical Values
Shore D	ASTM D2240	81

Other	Norm	Typical Values
Water Absorption, Short Term (24 hours)	ASTM D570	0.23%

1) Determined with TA-Instrument DHR rheometer, cone/plate, diameter 60 mm, shear rate 100 s⁻¹

The data contained in this publication are based on our current knowledge and experience. They do not constitute an agreed contractual quality of the product and, in view of the many factors that may affect processing and application of our products, do not relieve processors from carrying out their own investigations and tests. The agreed contractual quality of the product at the time of transfer of risk is based solely on the data in the specification data sheet. Any descriptions, drawings, photographs, data, proportions, weights, etc. given in this publication may change without prior information. The customer and/or user is responsible to consider and respect all hazard and safety issues according to the MSDS of Ultracur3D® EPD 1086 and take, implement and/or install adequate measures and precautions to avoid any personal injuries, property damages and/or environmental pollution. Therefore, Mass Additive Manufacturing GmbH shall not be liable for any personal injury, property damages and/or environmental emissions arising out of or related to the testing, handling or usage, storage and possession of Ultracur3D® EPD 1086. It is the sole responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed (02/2020)

Version 1.6

Mass Additive Manufacturing GmbH sales@forward-am.com www.forward-am.com

Photocentric

UK - Cambridge House, Oxney Road, Peterborough, PE1 5YW. +44 1733 349937. info@photocentric.co.uk
USA - 2205 West Parkside Lane, Phoenix, 85027, AZ. (623) 581-3220. info@photocentricusa.com

www.photocentricgroup.com